



(43) International Publication Date 16 December 2004 (16.12,2004)

(10) International Publication Number WO 2004/109825 A2

(51) International Patent Classification7:

H01M 4/58

(21) International Application Number:

PCT/JP2004/008157

(22) International Filing Date:

4 June 2004 (04.06.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 2003-160709 60/477,755

5 June 2003 (05.06.2003) JP 12 June 2003 (12.06.2003) US

(71) Applicant (for all designated States except US): SHOWA DENKO K.K. [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): NANBA, Youichi [JP/JP]; c/o Corporate R & D Center, Showa Denko K.K., 5-1, Okawacho, Kawasaki-ku, Kawasaki-shi, Kanagawa 210-0858 (JP). TAKEUCHI, Masataka [JP/JP]; c/o Corporate R & D Center Showa Denko K.K., 5-1 Okawacho, Kawasaki-Ku, Kawasaki-Shi, Kanagawa 210-0858 (JP). SUDOH, Akinori [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850, Oaza Omachi, Omachi-Shi, Nagano 398-0002 (JP). IINOU, Satoshi [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850, Oaza Omachi, Omachi-shi, Nagano 398-0002 (JP).

(74) Agent: OHIE, Kunihisa; Ohie Patent Office, Selva-Ningyocho 6F, 14-6, Nihonbashi-Ningyocho 2-chome, Chuo-ku, Tokyo 103-0013 (JP).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CARBON MATERIAL FOR BATTERY ELECTRODE AND PRODUCTION METHOD AND USE THEREOF

(57) Abstract: The invention relates to a carbon material for forming a battery electrode, comprising carbon powder having a homogeneous structure which is produced by causing an organic compound, serving as a ra.w material of a polymer, to deposit onto and/or permeate into carbonaceous particles, and subsequently polymerizing the organic compound, followed by thermal treatment at a temperature of 1,800 to 3,300°C, which comprises a structure which is substantially uniform throughout the entirety of the particle from the surface to the central core where a graphite crystal structure region and an amorphous structure region are distributed. By using the material, a battery having high discharging capacity and low irreversible capacity, with excellent coulombic efficiency and excellent cycle characteristics can be fabricated.

(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 16 December 2004 (16.12.2004)

PCT

(10) International Publication Number WO 2004/109825 A3

(51) International Patent Classification7: 8/02, C01B 31/02, 31/04

H01M 4/58.

(21) International Application Number:

PCT/JP2004/008157

(22) International Filing Date: 4 June 2004 (04.06.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

2003-160709 5 June 2003 (05.06.2003) 60/477,755 12 June 2003 (12.06.2003)

- (71) Applicant (for all designated States except US): SHOWA DENKO K.K. [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): NANBA, Youichi [JP/JP]; c/o Corporate R & D Center, Showa Denko K.K., 5-1, Okawacho, Kawasaki-ku, Kawasaki-shi, Kanagawa 210-0858 (JP). TAKEUCHI, Masataka [JP/JP]; c/o Corporate R & D Center Showa Denko K.K., 5-1 Okawacho, Kawasaki-Ku, Kawasaki-Shi, Kanagawa 210-0858 (JP). SUDOH, Akinori [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850, Oaza Omachi, Omachi-Shi, Nagano 398-0002 (JP). IINOU, Satoshi [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850, Oaza Omachi, Omachi-shi, Nagano 398-0002 (JP).

- (74) Agent: OHIE, Kunihisa; Ohie Patent Office. Selva-Ningyocho 6F, 14-6, Nihonbashi-Ningyocho 2-chome, Chuo-ku, Tokyo 103-0013 (JP).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

(88) Date of publication of the international search report: 17 November 2005

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CARBON MATERIAL FOR BATTERY ELECTRODE AND PRODUCTION METHOD AND USE THEREOF

(57) Abstract: The invention relates to a carbon material for forming a battery electrode, comprising carbon powder having a homogeneous structure which is produced by causing an organic compound, serving as a ra.w material of a polymer, to deposit onto and/or permeate into carbonaceous particles, and subsequently polymerizing the organic compound, followed by thermal treatment at a temperature of 1,800 to 3,300°C, which comprises a structure which is substantially uniform throughout the entirety of the particle from the surface to the central core where a graphite crystal structure region and an amorphous structure region are distributed. By using the material, a battery having high discharging capacity and low irreversible capacity, with excellent coulombic efficiency and excellent cycle characteristics can be fabricated. The carbon material of the invention may contain carbon fiber filaments. Average roundness, BET specific surface area, true density, laser Roman R value, and average particle size were investigated.

